



RISHABH RESINS & CHEMICALS

(AN ISO 9001:2015 CERTIFIED COMPANY)

Plot No. 15 E & F, SVCIE, IDA JEEDIMETLA,
HYDERABAD - 500055, (TS)

Ph No : 040-40213105 | (+91) 9391023105 | (+91) 9100953109

GST NO : 36AAMPJ0213G1Z4

Email : rishabhresins@gmail.com, nilesh@rishabhgroup.com ||
Website : www.rishabhresins.com



CERTIFICATE OF ANALYSIS SINGLE PACK OIL MODIFIED PU RESIN SILAC U210(60%)

Properties

Specifications

Appearance & Colour	: Urethane Oil Resin Single Pack Yellow Pale Colour
Oil Type	: Linseed Oil
Solid Content	: 60 (+/-) 2%
Specific Gravity @ 30°C	: 0.90 – 0.92
Viscosity @ 30°C in 50% Sol'n with	: 80 – 100 seconds
Mineral Sprit / MTO in B-4 Ford Cup	
Acid Value (mgm KOH/gm)	: < 4 (Free NCO < 0.01%)
Scratch Hardness after 48 hours	: ≥ 1500 gm's
Solvent Solubility	: Infinite in MTO/ Xylene/ Toluene
Resistance to Water & Chemicals	: Excellent
Colour @ 50% Sol'n	: 8 max'm on Gardner
Drying Time with Driers (30% solids)	
Solution in MTO/MS	: Surface Dry in Air: 20-30 Minutes Hard Dry: 90-120 Minutes At 150°C: 15-20 Minutes

**** Drying Time is measured at 30% solid solution in MTO with 2.0% Zirconium & 2.0% Cobalt as metals on solid contents.**